

DuPont™ Minlon®

mineral reinforced nylon resin

Minlon® 11C40 NC010

Minlon® 11C40 NC010 is a 40% mineral reinforced, heat stabilized polyamide 66 resin for injection molding.

Property	Test Method	Units	Value	
			DAM	50%RH
Identification				
Resin Identification	ISO 1043		PA66-IMD40	
Part Marking Code	ISO 11469		>PA66-IMD40<	
Mechanical				
Stress at Break	ISO 527	MPa (kpsi)	90 (13.0)	63 (9.2)
Strain at Break	ISO 527	%	10	35
Tensile Modulus	ISO 527	MPa (kpsi)	5900 (860)	2600 (377)
Poisson's Ratio			0.40	
Flexural Modulus	ISO 178	MPa (kpsi)	5400 (780)	2000 (290)
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m ²		
-30°C (-22°F)			4	
23°C (73°F)			7	12
Unnotched Charpy Impact Strength	ISO 179/1eU	kJ/m ²		
-30°C (-22°F)			85	100
23°C (73°F)			200	NB

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Minlon® are trademarks or registered trademarks of DuPont Company. Copyright© 2005.

050722/050722

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Minlon® 11C40 NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Thermal				
Deflection Temperature 0.45MPa	ISO 75f	°C (°F)	215 (419)	
1.80MPa			100 (212)	
Melting Temperature 10°C/min	ISO 11357-1/-3	°C (°F)	256 (493)	
CLTE, Normal -40 - 23°C (-40 - 73°F)	ISO 11359-1/-2	E-4/C (E-4/F)	0.53 (0.29)	
23 - 55°C (73 - 130°F)			0.65 (0.36)	
55 - 160°C (130 - 320°F)			0.98 (0.54)	
CLTE, Parallel -40 - 23°C (-40 - 73°F)	ISO 11359-1/-2	E-4/C (E-4/F)	0.53 (0.29)	
23 - 55°C (73 - 130°F)			0.64 (0.36)	
55 - 160°C (130 - 320°F)			0.80 (0.44)	
Electrical				
Relative Permittivity 1E2 Hz	IEC 60250		4.2	
1E6 Hz			3.9	
Volume Resistivity	IEC 60093	ohm m	1E11	
Dissipation Factor 1E2 Hz	IEC 60250	E-4	100	
1E6 Hz			100	
Electric Strength 2.0mm	IEC 60243-1	kV/mm (V/mil)	24 (610)	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Minlon® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050722/050722

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Minlon® 11C40 NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Flammability				
Flammability Classification 0.81mm	IEC 60695-11-10		HB	
Flammability Classification 0.81mm	UL94		HB	
Oxygen Index	ISO 4589-1/-2	%	26	
High Amperage Arc Ignition Resistance 0.81mm	UL 746A	arcs	>200	
1.5mm			>200	
Hot Wire Ignition 0.81mm	UL 746A	s	8	
1.5mm			16	
Temperature Index				
RTI, Electrical 0.81mm	UL 746B	°C	65	
RTI, Impact 0.81mm	UL 746B	°C	65	
RTI, Strength 0.81mm	UL 746B	°C	65	
Other				
Density	ISO 1183	kg/m ³ (g/cm ³)	1470 (1.47)	
Water Absorption Equilibrium 50%RH	ISO 62, Similar to	%	1.6	
Immersion 24h			1.1	
Saturation, immersed			6.0	
Molding Shrinkage Normal, 2.0mm	ISO 294-4	%	0.9	
Parallel, 2.0mm			0.9	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Minlon® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050722/050722

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Minlon® 11C40 NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Other				
Mold Shrinkage		%		
Flow, 1.6mm (0.063in)			0.9	
Flow, 3.2mm (0.126in)			0.9	
Flow, 6.4mm (0.25in)			1.4	
Transverse, 1.6mm (0.063in)			0.9	
Transverse, 3.2mm (0.126in)			0.9	
Transverse, 6.4mm (0.25in)			1.4	
Processing				
Melt Temperature Range		°C (°F)	285-305 (545-580)	
Melt Temperature Optimum		°C (°F)	295 (560)	
Mold Temperature Range		°C (°F)	70-120 (160-250)	
Mold Temperature Optimum		°C (°F)	100 (210)	
Drying Time, Dehumidified Dryer		h	2-4	
Drying Temperature		°C (°F)	80 (175)	
Processing Moisture Content		%	<0.20	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Minlon® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050722/050722

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.