

# DuPont™ Zytel®

nylon resin

## Zytel® 70G13HS1L BK031

Zytel® 70G13HS1L BK031 is a 13% glass fiber reinforced, heat stabilized, black polyamide 66 resin for injection molding.

| Property                       | Test Method    | Units             | Value       |            |
|--------------------------------|----------------|-------------------|-------------|------------|
|                                |                |                   | DAM         | 50%RH      |
| <b>Identification</b>          |                |                   |             |            |
| Resin Identification           | ISO 1043       |                   | PA66-GF13   |            |
| Part Marking Code              | ISO 11469      |                   | >PA66-GF13< |            |
| <b>Mechanical</b>              |                |                   |             |            |
| Stress at Break                | ISO 527        | MPa (kpsi)        | 120 (17.4)  | 75 (10.8)  |
| Strain at Break                | ISO 527        | %                 | 2.7         | 12         |
| Tensile Modulus                | ISO 527        | MPa (kpsi)        | 5500 (800)  | 3500 (508) |
| Flexural Modulus               | ISO 178        | MPa (kpsi)        | 4900 (710)  |            |
| Flexural Strength              | ISO 178        | MPa (kpsi)        | 190 (27.6)  | 100 (14.5) |
| Notched Charpy Impact Strength | ISO 179/1eA    | kJ/m <sup>2</sup> |             |            |
| -40°C (-40°F)                  |                |                   | 4.5         |            |
| 23°C (73°F)                    |                |                   | 5           |            |
| <b>Thermal</b>                 |                |                   |             |            |
| Deflection Temperature         | ISO 75f        | °C (°F)           |             |            |
| 0.45MPa                        |                |                   | 258 (496)   |            |
| 1.80MPa                        |                |                   | 238 (460)   |            |
| Melting Temperature            | ISO 11357-1/-3 | °C (°F)           |             |            |
| 10°C/min                       |                |                   | 262 (504)   |            |

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2005.

050320/050321

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Zytel® 70G13HS1L BK031

| Property  | Test Method    | Units                                  | Value                                     |       |
|---|----------------|--|---|-------|
|   |                |  | DAM                                       | 50%RH |
| <b>Thermal</b>  |                |  |   |       |
| CLTE, Normal<br>-40 - 23°C (-40 - 73°F)<br>23 - 55°C (73 - 130°F)<br>55 - 160°C (130 - 320°F)   | ISO 11359-1/-2 | E-4/C (E-4/F)                          | 0.77 (0.43)<br>0.96 (0.53)<br>1.58 (0.88) |       |
| CLTE, Parallel<br>-40 - 23°C (-40 - 73°F)<br>23 - 55°C (73 - 130°F)<br>55 - 160°C (130 - 320°F) | ISO 11359-1/-2 | E-4/C (E-4/F)                          | 0.42 (0.23)<br>0.40 (0.22)<br>0.27 (0.15) |       |
| <b>Electrical</b>   |                |  |   |       |
| CTI<br>3.0mm  | UL 746A        | V                                      | >600                                      |       |
| <b>Flammability</b>   |                |  |   |       |
| Flammability Classification<br>0.71mm   | UL94           |  | HB  |       |
| High Amperage Arc Ignition Resistance<br>0.71mm   | UL 746A        | arcs                                   | >200                                      |       |
| Hot Wire Ignition<br>0.71mm<br>1.5mm<br>3.0mm   | UL 746A        | s                                      | 12<br>7<br>8                              |       |
| <b>Temperature Index</b>  |                |  |   |       |
| RTI, Electrical<br>0.71mm   | UL 746B        | °C                                     | 140                                       |       |
| RTI, Impact<br>0.71mm   | UL 746B        | °C                                     | 125                                       |       |
| RTI, Strength<br>0.71mm   | UL 746B        | °C                                     | 140                                       |       |
| <b>Other</b>  |                |  |   |       |
| Density   | ISO 1183       | kg/m <sup>3</sup> (g/cm <sup>3</sup> ) | 1230 (1.23)                               |       |
| Molding Shrinkage<br>Normal, 2.0mm<br>Parallel, 2.0mm   | ISO 294-4      | %                                      | 1.0<br>0.5                                |       |

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.  
ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.  
Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050320/050321

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

## Zytel® 70G13HS1L BK031

| Property                        | Test Method | Units   | Value             |       |
|---------------------------------|-------------|---------|-------------------|-------|
|                                 |             |         | DAM               | 50%RH |
| <b>Processing</b>               |             |         |                   |       |
| Melt Temperature Range          |             | °C (°F) | 285-305 (545-580) |       |
| Melt Temperature Optimum        |             | °C (°F) | 295 (565)         |       |
| Mold Temperature Range          |             | °C (°F) | 70-120 (160-250)  |       |
| Mold Temperature Optimum        |             | °C (°F) | 100 (210)         |       |
| Drying Time, Dehumidified Dryer |             | h       | 2-4               |       |
| Drying Temperature              |             | °C (°F) | 80 (175)          |       |
| Processing Moisture Content     |             | %       | <0.20             |       |

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050320/050321

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.