



PA6G30HSNC201

6+30%

General Information		
	30%	6
Product Describe	30% Glass Fiber Reinforced PA6	

Grade

		Testing Standard
Mechanical Properties		
Tensile Strength	194 MPa	ISO527, 50mm/min
Elongation at break		ISO527, 50mm/min
Flexural Strength	278 MPa	ISO178, 2mm/min
Flexural Modulus	8921 MPa	ISO178, 2mm/min
Charpy Impact notched	15.2 KJ/m ²	ISO179
Charpy Impact unnotched	97.5 KJ/m ²	ISO179
Rockwell Hardness		ISO2039/2